



Product name : Holding color foundation

Sample No : 20180817A

Formulation :

	Ingredient Name	INCI Name	%
A.	KF-995	Cyclopentasiloxane	22.00
	XIAMETER™PMX-200 Silicone Fluid 5.0 cSt	Dimethicone	5.00
	UNIFILMA HVY	Dextrin Isostearate	5.00
	Purolan IHD	Isohexadecane	5.00
	Dow Corning®556 Cosmetic Grade Fluid	Phenyl Trimethicone	1.50
	Emalex DISG-3	Polyglyceryl-3 Diisostearate	1.00
	EMALEX SS-5051	PEG-10 Dimethicone /Dimethicone	5.50
	EMALEX DAPE-0207	PPG-2-Deceth-7	0.50
	KSG-210	Dimethicone (and) Dimethicone/PEG-10/15 Crosspolymer	0.80
	SALACOS DP-518N	Dipentaerythrityl Pentaisostearate	1.50
	TOCOPHEROL 80	TOCOPHEROL	0.20
	ADEKA NOL OG	Caprylyl Glycol	0.20
	Phenoxyethanol	Phenoxyethanol	0.20
B.	HDK H20	Silica Dimethyl Silylate	1.50
	S-Ben(W)	Quaternium-18 Bentonite	1.50
	Landpowder si1018	Titanium Dioxide / Talc /Dimethicone / Iron Oxide	10.00
	ETERPEARL WJ 450	Polymethylsilsesquioxane	2.00
	ETERAC P-CM-5	Polymethyl Methacrylate	1.00
	SAMT-Z1	Ultrafine zinc oxide / Myristic acid / Dimethicone	2.20
	SA-UT-A40 Powder	MiBrid Titanium dioxide / Dimethicone /Aluminum Hydroxide / Stearic	4.00
C.	1,3-BG	Butylene Glycol	2.00
	WSK	Tremella Fuciformis Sporocarp Extract	0.05
	Deionized Water	Water	15.75
D.	MgSO ₄ ·7H ₂ O	Magnesium Sulfate	0.50
	EDTA-2Na	Disodium EDTA	0.05
	Deionized Water	Water	10.00
E.	IZAYOI	Butylene Glycol / Water / Rosa Roxburghii Fruit Extract	0.50
	Cinderella Care	Butylene Glycol / Water / Thymus Serpillum Extract	0.50
	Perfume No. 16716	Fragrance	0.05

Prepare by Emily 2018/8/17

香林企業股份有限公司 KALIN ENTERPRISE CO.,LTD



Procedure :

1. Heat UNIFILMA HVY and Purolan IHD to 60 °C, stir and dissolve, and then cool to room temperature.
2. Using a dispersion mill, mix and dissolve A phase for 10 minutes at 700rpm.
3. Mix and dissolve C phase at room temperature.
4. Mix and dissolve D phase at room temperature.
5. Using a dispersion mill, add B phase to 【2】 at 700~1000rpm.
6. Using a dispersion mill, add 【3】 and 【4】 to 【5】 and emulsify for 3 minutes at 2000~3000rpm after homogenizer for 3 minutes at 3500rpm.
7. Cool to 40°C, add E phase to 【6】 , with paddle mixing.

※This formula is for reference only. If it needs to be commercialized, please confirm the relevant test

Prepare by Emily 2018/8/17

香林企業股份有限公司 KALIN ENTERPRISE CO.,LTD

總公司:11670臺北市文山區景文街46-1號10樓

電話:+886 289313301 傳真:+886 289313323 統編:70840978

怡滬國際貿易(上海)有限公司

香霖國際貿易(廣州)有限公司

電話: + 86 21 54240077

電話: + 86 20 38889468